

## **High Fire Clays**

## **PRA - White High Fire Clay**

	-	Cone 03
	In	Cone ob
	the att	
	-t-	
		a serie for a for
	10 DA	Cone 5
	may your 1	
	1 10 200	
10 - 10 - C		
		Stern and
	5	Cone 10
	Time into 1	
	S. Strand	
Charles F		3
	The second	And And
	and the second	and the second second
	AND TOURS	Standard Caller

## PRAF

Item number: 13 320 200 | UPC: 8422830133017



## White Sculpture/Raku Clay with Fine Grog

White sculpture and Raku clay body with 40% fine grog (up to 35 Mesh). Formulated for artistic ceramics, it is ideal for sculpture, murals and Raku pieces. The high content of grog confers a beautiful textured surface and an excellent behavior during drying and firing. Its particular ivory color after firing is much appreciated and provides an excellent ware for glazes and coloring oxides, which develop bright and intense tones. It is also known as "Rafael" clay, and it is very popular because of its excellent behavior for Raku. Available in extruded body (moist form).

Firing range: **Cone 6-10 (2269°-2381°F)** Biscuit: Cone 06 (1855°F) Water content: 17% Plasticity (IP Atterberg): 16 Carbonate content (CaCO3): 0% Drying shrinkage: 5.4% Firing shrinkage at Cone 10: 4.6% Porosity (water absorption) at Cone 10: 4.1% Dry bending strength: 2.4 N/mm2 Fired bending strength at Cone 10: 26.2 N/mm2 Thermal coefficient (a25-500°C): 55.9x10-7°C-1

Tilm-wrapped pack + carton box | 📥 27.6 lb (12.5 kg)



CERÁMICA COLLET S.A. | Fundada en 1874 Polígono Industrial L'Olana, S/N. E-08292 Esparreguera - Barcelona (SPAIN) T +34 93 777 23 44 | F +34 93 770 94 11 | info@sio-2.com | www.sio-2.com